

**Tiles / Direct Screen Printing  
Bright Gold (UV-curing)**

| Colour         | Product     | Precious Metal Content | Firing Range 780-820°C/1436-1508°F<br>Shock Firing | Notes |
|----------------|-------------|------------------------|--|-------|
| yellow         | GPP 2344/UV | 9%                     | ●  | -     |
| reddish yellow | GPP 2343/UV | 7%                     | ●  | -     |

**Tiles / Direct Screen Printing  
Bright Platinum (UV-curing)**

| Colour   | Product     | Precious Metal Content | Firing Range 1180-1230°C/2126-2246°F<br>Shock Firing | Notes |
|----------|-------------|------------------------|--|-------|
| platinum | GPP 4329/UV | 7%                     | ●  | -     |